



# RM Alkon Stahl

Stevana Brakusa 4, 11030 Beograd - tel.7540-847 \* fax.3055-488

e-mail: office@rmalkon.co.rs \* www.rmalkon.co.rs

## NERĐAJUĆI ČELICI - UPOREDNA TABELA KVALITETA

EN / W.Nr.	DIN	AISI	SS	JUS	Ravne
1.4005	X12 CrS 13	416	2380		
1.4006	X12 Cr 13	410	2302	Č.41701	
1.4016	X6 Cr 17	430	2320	Č.4174	
1.4021	X20 Cr 13	420	2303	Č.4172	PK 3
1.4024	X15 Cr 13	420 (SAE)		Č.4171	PK 2
1.4028	X30 Cr 13	420 F	2304	Č.4173	
1.4034	X46 Cr 13		(2304)	Č.4175	
1.4057	X17 CrNi 16-2	431	2321	Č.4570	PK 2 SP
1.4104	X14 CrMoS 17	430 F	2383	Č.4790	
1.4112	X90 CrMoV 18	440 B		Č.4772	
1.4122	X39 CrMo 17-1				
1.4301	X5 CrNi 18-10	304	2332	Č.4580	PK 11 EX
1.4305	X8 CrNiS 18-9	303	2346	Č.4590	
1.4306	X2 CrNi 19-11	304 L	2352	Č.45701	
1.4307	X2 CrNi 18-9	304 L	2352		
1.4310	X10 CrNi 18-8	301	2331	Č.4571	
1.4362	X2 CrNiN 23-4	S 32304	2327	SAF 2304 ® - Sandvik AB	
1.4401	X5 CrNiMo 17-12-2	316	2347	Č.4573	PK 12
1.4404	X2 CrNiMo 17-12-2	316 L	2348	Č.45703	
1.4410	X2 CrNiMoN 25-7-4	S 32750	2328	SAF 2750 ® - Sandvik AB	
1.4432	X2 CrNiMo 17-12-3	316 L	2353		
1.4435	X2 CrNiMo 18-14-3	316 L	2353	Č.45704	
1.4436	X3 CrNiMo 17-13-3	316	2343	Č.45706	
1.4438	X2 CrNiMo 18-15-4	317 L	2367	Č.45705	
1.4439	X2 CrNiMoN 17-13-5	(317 LMN)		Č.47702	
1.4449	X5 CrNiMo 17-13	317			
1.4460	X3 CrNiMoN 27-5-2	329	2324	4460 - duplex	
1.4462	X2 CrNiMoN 22-5-3	S 32205	2377	2205 - duplex	
1.4529	X1 NiCrMoCuN 25-20-7				
1.4539	X1 NiCrMoCu 25-20-5	(904 L)	2562		
1.4541	X6 CrNiTi 18-10	321	2337	Č.4572	PK 11 SP
1.4547	X1 CrNiMoCuN 20-18-7	S 31254	2378	254 SMO ® - Outokumpu	
1.4550	X6 CrNiNb 18-10	347	2338	Č.4582	PK 11 NB
1.4563	X1 NiCrMoCu 31-27-4		2584		
1.4571	X6 CrNiMoTi 17-12-2	316 Ti	2350	Č.4574	PK 12 SP
1.4652	X1 CrNiMoMnN 24-22-8	S 32654		654 SMO ® - Outokumpu	
1.4724	X10 CrAlSi 13			Č.4972	PK 924
1.4742	X10 CrAlSi 18			Č.4973	PK 925
1.4749	X18 CrN 28	446-1	2322		
1.4762	X10 CrAlSi 25	(446)	(2320)	Č.4970	PK 10
1.4821	X15 CrNiSi 25-4			Č.4586	
1.4828	X15 CrNiSi 20-12	309		Č.4577	
1.4841	X15 CrNiSi 25-21	314		Č.4578	PK 19
1.4835	X9 CrNiSiNCe 21-11-2	S 30815	2368	253 MA ® - Outokumpu	
1.4845	X8 CrNi 25-21	310 S	2361		
1.4864	X12 NiCrSi 35-16	330		Č.4579	PK 20